

**RETICULATED POLYURETHANES**

<b>POROSITY (PPI)</b>	<b>DENSITY (LB/cu.FT)</b>	<b>TENSILE STRENGTH (PSI)</b>	<b>ULTIMATE ELONGATION (%)</b>	<b>TEAR STRENGTH (LB/IN)</b>	<b>FIRE RATING</b>
SIF 10	1.90	20	315	5.5	UL-900 CLASS 2
SIF 20	1.90	25	320	5.5	UL-900 CLASS 2
SIF 30	1.90	25	320	5.3	UL-900 CLASS 2
SIF 45	1.90	28	340	4.7	UL-900 CLASS 2
SIF 60	1.90	33	402	4.3	UL-900 CLASS 2
SIF 80	1.90	35	415	3.9	UL-900 CLASS 2
SIF 100	1.90	35	415	3.9	UL-900 CLASS 2
SIF FELT 3-900	5.25	50-80	250-350	5-10	UL-900 CLASS 2
SIF FELT 10-900	17.5	160-200	200-300	20-30	UL-900 CLASS 2
SIF FELT 15-900	26.2	220-270	200-300	25-35	UL-900 CLASS 2

This information is presented to our best knowledge. All test data are average values unless stated and should be considered as guidelines to the performance of this product and should not be used as specifications.