

**NON-RETICULATED POLYURETHANES**

Description	Density (LB/cu.FT)	Tensile Strength (PSI)	Ultimate Elongation (%)	Compression Set 90% 22 hrs., 158F	Fire Rating
1.2 Polyether	1.25	10	125	15 Max	None
1.5 Polyether	1.4-1.6	15	150	10 Max	None
2.0 Polyether	1.85	12	150	150 Max	UL-94 HF-1
2.0 Polyester	1.85	18	120	15 Max	UL-94 HF-1
4.0 Polyester	3.9	24	200	15 Max	UL-94 HF-1
6.0 Polyester	5.75	18	150	15 Max	UL-94 HF-1

This information is presented to our best knowledge. All test data are average values unless stated and should be considered as guidelines to the performance of this product and should not be used as specifications.