



MERRYWEATHER FOAM, INC.

An ISO9002 Certified Company

Description	Density (LB/cu.FT)	25% Compression Deflection (PSI)	Temperature Range (%)	Tensile Strength (PSI) (typical)	Typical Elongation (%)
SCE-41 Black Sponge	4.5-6.5	2-5	-70F To 158F	50	150
SCE-42 Black Sponge	4.5-6.5	5-9	-70F To 158F	50	150
SCE-43 Black Sponge	8-13	9-13	-70F to 225F	70	120
RE-41 Black EPDM	9-14	2-5	-90F To 275F	80	180

This information is presented to our best knowledge. All test data are average values unless stated and should be considered as guidelines to the performance of this product and should not be used as specifications.